

**PROJECT NUMBER:** 3018 98-75790.1

**PAGE:** 1 of 2

**DATE:** October 15, 1998

## **SOUND ABSORPTION - ASTM C423-90a**

### **INTRODUCTION:**

This report presents the results of a Noise Reduction Coefficient (NRC) test conducted on a 1" Wall Panel manufactured and submitted on October 7, 1998 and was conducted on October 13, 1998.

This report must not be reproduced except in its entirety with the approval of Maxim Technologies, Inc. The data in this report relates only to the item tested.

Maxim Technologies, Inc. has been accredited by the U.S. Department of Commerce and the National Institute of Standards and Technology (NIST, formerly NBS) under their National Voluntary Laboratory Accreditation Program (NVLAP) for conducting this test procedure. This report may not be used to claim product endorsement by NVLAP or any agency of the U.S. Government

### **SUMMARY OF RESULTS:**

The NRC of the panel described below is **0.85**. (See individual frequency values below under TEST RESULTS).

### **SPECIMEN IDENTIFICATION:**

Manufacturer :	Rendered by Manufacturer for Technature Inc.
Type :	1" Wall Panel
Nom. Dimensions (W x H x D) :	4' x 8' x 1"
Weight :	1.0 lbs. each specimen (0.66 PSF)
Surface Area :	32 ft <sup>2</sup> each specimen.
Total Surface Area Tested :	64 ft <sup>2</sup> consisting of 2 specimens.
Mounting Type :	On floor with 1/4" air space beneath. Edges taped.
Specimen Description :	Acoustical Wall Panel, 1" thick 6.0 PCF, Fiberglass Core, 100% Polyester Facing.

**PROJECT NUMBER:** 3018 98-75790.1

**PAGE:** 2 of 2

**DATE:** October 15, 1998

**TEST METHOD:**

ASTM C 423-90a, "Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method" was followed in every respect.

Absorption coefficients are the fraction of diffuse incident sound absorbed by the specimen and are expressed in sabins per square foot. The NRC is the average of the absorption coefficients for 250, 500, 1000, and 2000 Hertz and is reported to the nearest integral of 0.05.

The temperature and relative humidity of the chamber during the tests were 72°F and 58%, respectively.

**TEST EQUIPMENT:**

<b><u>Manufacturer</u></b>	<b><u>Model</u></b>	<b><u>Serial #</u></b>	<b><u>Description</u></b>
Norwegian Electronics	NE830	11511	Real Time Spectrum Analyzer
Brüel & Kjær	3923	815424	Rotating Microphone Boom
Larson-Davis	2560	1032	Pressure Condenser Microphone

**1" Wall Panel**

<b>Frequency Hz</b>	<b>Abs. Coefficients</b>	<b>Uncertainty %</b>
<b>125</b>	0.14	6.1
<b>250</b>	0.27	2.4
<b>500</b>	0.80	1.5
<b>1000</b>	1.11	1.0
<b>2000</b>	1.14	0.8
<b>4000</b>	1.14	0.8

**Noise Reduction Coefficient (NRC) = 0.85**

Freq. = Octave band center frequency.

Abs. Coefficient = Sound absorption coefficient (extended plane applications)

Uncertainty = % uncertainty of the absorption coefficient for 95% confidence